PRODUCT **DATA SHEET**

Bisalloy ARMOUR

BISALLOY® ARMOUR RHA360 STEEL

Introduction

BISALLOY® ARMOUR RHA360 steel (Rolled Homogeneous Armour) - a quenched and tempered steel armour plate, possessing very good weldability, suitable for use in both military and civil applications where high rates of shock loading and resistance to penetration by ballistic projectiles are required.

Brinell hardness

Thickness (mm)	Specification	Typical
5 - 50[1]	310-410 HB[2]	350 HB

[1] Other thicknesses may be available on application

[2] Hardness range varies depending on thickness

Tensile properties

Property	Typical
0.2% Proof Stress	1040 MPa
Tensile Strength	1140 MPa
Elongation in 50 mm GL	15%

Charpy impact values

Thickness (mm)	Test Piece	Test Temp	Min. Energy (Transverse)	Min. Energy (Longitudinal)
5	10 x Thk	-40°C	By Agreement	By Agreement
6 - <8	10 x 5	-40°C	12J[3]	12J[3]
8 - <12	10 x 7.5	-40°C	17J[3]	17J[3]
≥12	10 x 10	-40°C	22J[3]	22J[3]

[3] Minimum average energy will vary depending on hardness

Chemistry

The chemical specification conforms to the requirements of MIL-DTL-12560, although it is tighter than the requirements of that specification so as to optimise the material's performance. Product chemical analyses are taken on a per-heat basis. Chemical analysis is as follows:

Chemical composition

Thickness (mm)	Weight %	C	P[4]	Mn	Si	S[4]	Ni	Cr	Mo	B	CE(IIW)	CET
5 - 50	Maximum	0.27	0.020	1.50	0.60	0.005	0.50	1.20	0.30	0.002	0.61*	0.40*

[4] P + S ≤ 0.020%

* Typical for 12mm plate

Thickness tolerance

Thickness (mm)	Special Tolerance
5 - 25	-0.0 + 1.0
>25 - 50	-0.0 + 1.2

BISALLOY is a registered trade mark of Bisalloy Steels Group Limited, ABN 22 098 674 545

PRODUCT **DATA SHEET**

Bisalloy ARMOUR

BISALLOY® ARMOUR RHA360 STEEL

Test frequency

Per Plate	Per Batch	By Agreement
Hardness	Charpy (L), Charpy (T)	Thickness, Tensile, Ballistic Properties, Product Analysis

Other

Equivalent Specification	Surface Finish
MIL - DTL - 12560 class 1	Shotblasted

Fabrication

For advice on fabrication refer to relevant Bisalloy technical brochures.
Contact Bisalloy direct or visit www.bisalloy.com

PLEASE NOTE: Every care has been taken to ensure the accuracy of information contained in this manual which supersedes earlier publications, however Bisalloy Steels shall not be liable for any loss or damage whatsoever caused from the application of such information. Typical values are provided for reference information only and no guarantee is given that a specific plate will provide these properties. Information is subject to change without notice. **Published September 2025**

BISALLOY is a registered trade mark of Bisalloy Steels Group Limited, ABN 22 098 674 545